

Technical Specification for 80*160 cm		
<u>SR NO</u>	<u>CHARACTERISTICS</u>	<u>VARMROA VALUES</u>
A	Dimension & Surface Quality	
1	Deviation in Length and Width	+ / - 0.1 %
2	Deviation in Thickness	+ / - 3.50 %
3	Straightness of sides	+ / - 0.1 %
4	Rectangularity	+ / - 0.1 %
5	Surface Flatness	+ / - 0.2 %
6	Color Differences	No Change
7	Surface Coating	Nano Polished
B	Physical Properties	
1	Water Absorption	0.08%
2	Flexural Strength (MOR)	> 40 N / mm ²
3	Mohs Hardness	5 Mohs
4	Flexural Breaking Strength	> 1700 N
5	Bulk Density (gm / cc)	2.35 gm/cc
6	Glossiness	min 85 % reflection
7	Slip Resistance Coefficient of Friction	> 0.6
8	Crazing Resistance	Passes 4 Cycle
9	Resistance of Surface Abrasion	> PEI I V
C	Chemical Properties	
1	Staining resistance	Resistant
2	HouseHold Chemicals	No Damage
D	Thermal Properties	
1	Thermal Shock Resistance	No Damage
2	Thermal Expansion	6 x 10 ⁻⁶
3	Moisture Expansion	Nill



VARMORA GRANITO PVT. LTD.

Head Office : 8-A, National Highway, At. Dhuva, Tal. Wankaner, Dist. Morbi (Gujarat) India. Tel. : +91-98252 23068, E-mail : info@varmora.com
 Corporate Office : A-54, 1st Floor, Elite Auto House, Mathurdas Vasanji Road, Andheri - Kurla Road, Andheri (E), Mumbai-400093,
 Tel. : +91-22-28389790/91/92, Fax : +91-22-28389794, E-mail : mumbai@varmora.com Visit us at : www.varmora.com
 Office : 5-Savsar plot, Opp. Priydarshini Complex, Nr. old Bus Stand, Morbi - 363 641, Gujarat, INDIA.

C.I.No. : U26914GJ2003PTC043194