

## PRODUCT DATA SHEET

|  |                             |                |                |
|--|-----------------------------|----------------|----------------|
| <b>ITEM:</b>   | VIEW NEVE SATIN RECTIFICADO | <b>BRAND:</b>  | BALDOCER, S.A. |
| <b>DATE:</b>   | 29/04/2021                  | <b>FORMAT:</b> | 40X120 cm      |
| <b>CLASSIFICATION OF FINISHED PRODUCT (UNE-EN-14411)</b> |                             | <b>GROUP:</b>  | BIII           |
|  |                             | <b>ANNEX:</b>  | L              |

### FACIAL DIMENSIONS RANGE AND SURFACE QUALITY

|                           | UNE-EN-ISO-10545-2 | REFERENCE       | RESULT                     |
|---------------------------|--------------------|-----------------|----------------------------|
| DIMENSIONS                |                    |                 | 400X1200                   |
| LENGTH                    |                    | ± 0,5 %         | 0,05% / -0,01%<br>1200 mm  |
| WIDTH                     |                    | ± 0,5 %         | 0,02% / -0,02%<br>400,1 mm |
| STRAIGHTNESS OF SIDES     |                    | ± 0,3 %         | 0,03% / -0,03%             |
| THICKNESS                 |                    | ± 10,0 %        | 0,91% 11 mm                |
| RECTANGULARITY            |                    | ± 0,5 %         | 0,16% / -0,18%             |
| CENTRAL SURFACE FLATNESS  |                    | +0,5 % / -0,3 % | 0,15%                      |
| LATERAL SURFACE FLATNESS  |                    | +0,5 % / -0,3 % | 0,16%                      |
| DIAGONAL SURFACE FLATNESS |                    | ± 0,5 %         | 0,02% / -0,13%             |

### PHYSICAL PROPERTIES

|   | UNE-EN-ISO-10545-3 |                          |           |
|---|--------------------|--------------------------|-----------|
| WATER ABSORPTION                                    |                    | E > 10,0%                | 14%       |
|   | UNE-EN-ISO-10545-4 |                          |           |
| BREAKING STRENGTH                                   |                    | MIN 600 N                | 1441      |
| MODULUS OF RUPTURE                                  |                    | MIN 12 N/mm <sup>2</sup> | 22        |
|   | UNE-EN-ISO-10545-6 |                          |           |
| DETERMINATION TO ABRASION RESISTANCE. DEEP ABRASION |                    | NOT APPLY                | NOT APPLY |
|   | UNE-EN-ISO-10545-7 |                          |           |
| DETERMINATION TO ABRASION RESISTANCE                |                    | REVOLUTIONS              | PEI       |
|   |                    | ---                      | ---       |
|   | UNE-EN-ISO-10545-9 |                          |           |
| THERMAL SHOCK RESISTANCE                            |                    |                          | FULFILLED |

# BALDOCER

## UNE-EN-ISO-10545-11

|                    |  |           |
|--------------------|--|-----------|
| CRAZING RESISTANCE |  | FULFILLED |
|--------------------|--|-----------|

## UNE-EN-ISO-10545-12

|                  |  |               |
|------------------|--|---------------|
| FROST RESISTANCE |  | NOT FULFILLED |
|------------------|--|---------------|

## UNE 67101

|  |  |  |
|--|--|--|
| DETERMINATION HARDNESS TO SURFACE STRIPPING.MOHS |  |  |
|--|--|--|

## DETERMINATION OF SLIDING RESISTANCE

|  |       |     |
|--|-------|-----|
| VALUE FOLLOWING UNE 41901-EX (PENDULUM)        | CLASS | --- |
| VALUE FOLLOWING DIN 51130 (RAMP TEST)          | R     | --- |
| VALUE FOLLOWING DIN 51097 (RAMP TEST BAREFOOT) | CLASS | --- |
| VALUE FOLLOWING ANSI A 326.3 (DCOF-BOT 3000E)  |       |     |

## CHEMICAL PROPERTIES

## UNE-EN-ISO-10545-13

|  |  |           |
|--|--|-----------|
| CHEMICAL RESISTANCE                    |  | FULFILLED |
| HOUSEHOLD CHEMICALS                    |  | GA        |
| SWIMMING POOL SALTS                    |  | GA        |
| HYDROCHLORIC LOW CONCENTRATION         |  | GLA       |
| CITRIC ACID                            |  | GLA       |
| POTASSIUM HYDROXIDE LOW CONCENTRATION  |  | GLA       |
| HYDROCHLORIC HIGH CONCENTRATION        |  | GHA       |
| LACTIC ACID                            |  | GHA       |
| POTASSIUM HYDROXIDE HIGH CONCENTRATION |  | GHA       |

## UNE-EN-ISO-10545-14

|                         |  |           |
|-------------------------|--|-----------|
| RESISTANCE TO STAINS    |  | FULFILLED |
| IRON OXIDE-CHROME OXIDE |  | 5         |
| IODINE                  |  | 5         |
| OLIVE OIL               |  | 5         |

The test results of this sheet are made in our production plant with calibrated technology. However, we are non-official laboratory, for this reason all the results are exclusively informative and related to the tested tiles.

**BALDOCER, S.A.**  
Ctra. La Pobla Tornesa - V. d'Alba, Km. 4  
Tel: 902 456 700 - Fax 964 330 033  
12192 VILAFAMÉS (Castellón)