



PRODUCT CERTIFICATE

LABORATORY OF FINISHED PRODUCT

ISO 13006-10545
 Equivalent Brazilian Norm ABNT NBR ISO 13006 - NBR ISO 10545
 Brazilian Performance Norm ABNT - NBR 15575

Eliane Revestimentos Ceramicos Ltda . Rua Maximiliano Gaidzinski-sala 2, N. 245
 88845-000 . Cocal do Sul- SC . Brasil . +55 (048) 3447-7777 . www.eliane.com

Product:	BERNINI ORO PO 90X90	Manufacturing Process:	Wet ceramic process
Code:	8046169	Manufacturing Size:	900,0 x 900,0 mm
Class:	Bla	Nominal Size:	90X90 cm
Typology:	Porcelain tile	Thickness:	11,0 mm
Shade Variation:	V2	Coverage Area:	1,63m ² /box
Grout Joint:	1 mm	Pieces per box:	2,00
Rectified:	Yes	Surface:	GL (Glazed)



		CHARACTERISTICS	TESTING METHOD	SPECIFICATION		RESULTS
USAGE RECOMMENDATION	FIR	Indoor dry residential floors	Manufacturer's recommendation	ISO 13006:	± 5,00	FLC WRC WFA
	FLC	Indoor light commercial floors, including the areas FIR				
	FMC	Indoor medium commercial floors, including the areas FLC and FIR				
	FHC	Indoor heavy commercial floors, including the areas FMC, FLC, FIR				
	FFO	Flat outdoor floors				
	FRO	Outdoor inclines and ramps (maximum slope of 8.33%)				
	WID	Indoor dry residential and commercial walls				
	FWI	Indoor wet residential and commercial floors				
	WRC	Indoor and outdoor, wet or dry, residential and commercial walls, including the areas WID. For regions reaching below freezing temperatures, non frost resistant tiles are indoor only.				
	WWS	Swimming pool interior walls, including the areas WRC and WID				
WFA	External facades, including the areas WRC and WID					
DIMENSIONAL AND SURFACE PROPERTIES	Deviation of W/N:	W - Work size (mm) N - Nominal Size (mm) r - Average tile size (mm)	ISO 10545-2	ISO 13006:	± 5,00	± 5,00
	Deviation of r/W:	W - Work size (mm)	ISO 10545-2	ISO 13006:	± 1,00	± 1,00
	Deviation of e/eW:	e - Average tile thickness (mm) eW - Fabrication thickness (mm)	ISO 10545-2	ISO 13006:	10,50 - 11,50	10,50 - 11,50
	Rectangularity:	Deviation from W (mm)	ISO 10545-2	ISO 13006:	± 1,50	± 1,50
	Straightness of sides:	Deviation from W (mm)	ISO 10545-2	ISO 13006:	± 0,80	± 0,80
	Edge curvature:	Deviation from W (mm)	ISO 10545-2	ISO 13006:	± 1,80	± 1,80
	Centre Curvature:	Deviation from dW (mm)	ISO 10545-2	ISO 13006:	± 1,80	± 1,80
	Warpage:	Deviation from dW (mm)	ISO 10545-2	ISO 13006:	± 1,80	± 1,80
PHYSICAL PROPERTIES	Water Absorption:	(%)	ISO 10545-3	ISO 13006:	≤ 0,5	≤ 0,5
	Modulus of Rupture:	(MPa)	ISO 10545-4	ISO 13006:	≥ 35	≥ 40
	Breaking Strength:	(N)	ISO 10545-4	ISO 13006:	≥ 1300	≥ 2600
	Resistance to Cracking:	(Cycles)	ISO 10545-11	ISO 13006:	1	5
	Moisture Expansion:	(mm/m)	ISO 10545-10	ISO 13006:	≤ 0,6	≤ 0,2
	Coefficient of Restitution		ISO 10545-5	ISO 13006:	≥ 0,55	≥ 0,60

	CHARACTERISTICS		TESTING METHOD	SPECIFICATION	RESULTS	
CHEMICAL PROPERTIES	Stain Resistance					
	Penetrating Agent	Green Chrome (40% oil)	ISO 10545-14	ISO 13006:	≥ 3	
	Layer Forming Agent	Olive Oil				
	Oxidizing Agent	Alcoholic Iodine				
	Chemical Resistance					
	Domestic product	Ammonium Chloride 100g/L	ISO 10545-13	ISO 13006:	≥ GB	GA
	Pool water treatment	Sodium hypochlorite 20mg			≥ GB	GA
	Low concentration alkali	Potassium Hydroxide 30g / L			A declarar	GLB
	Low concentration acid	Chloridric acid 3% (v/v)			A declarar	GLB
	Low concentration acid	Citric Acid 100g/L			A declarar	GLB
DYNAMIC FRICTION COEFFICIENT	Wet Dynamic Friction Coefficient		NBR 16919-	NBR 16919:	< 0,40	≥ 0,30
PERFORMANCE	Solar Absorbance - α*		NBR 15575 - 3-	NBR 15575:	To declare	0.4 - 0.5
	Solar Deflection - ε*		NBR 15575 - 3-	NBR 15575:	To declare	0.75 - 0.85
	Impact of Hard Object		NBR 15575 - 3-	NBR 15575:	Ruptura (5J)	Ruptura (5J)
	Flammability		NBR 15575 - 3-	NBR 15575:	Class I	Class I
	Solar Reflectance - ρ*		NBR 15575 - 3-	NBR 15575:	To declare	0.6 - 0.5
	Moisture Resistance		NBR 15575 - 3-	NBR 15575:	To declare	Resistant
	Useful life:	(years)	NBR 15575 - 3-	NBR 15575:	20 fachada e 13 outros	20 fachada e 13 outros
	Solar Reflectance Index - SRI H = 5 (W / m ² K)*		NBR 15575 - 3-	NBR 15575:	To declare	80 - 65

Note:

Check if the product is suitable for the intended use.

Sand may cause scratches in any type of covering (stone, wood, vinyl or ceramic). For this reason, ceramic tile are not warranted against scratches, specially products with glossy finish. It is recommended special care during its installation and its use. In residential areas, we recommend to protect the base of furniture and appliances. Several performance characteristics required in the ABNT NBR 15575 norm refer to the prescriptive ABNT NBR 13818 norm, which is contained in this report.

Negligence towards the recommended use specified in this report, abnormal environmental and climate factors, changes in the work surroundings, will reduce the useful lifetime of the product, which may be shorter than the period declared by the manufacturer.

* According to information in the ANFACER sectorial performance manual



QR WARRANTY CODE:

Validate this certificate in:



COCAL DO SUL (SC), November 23th, 2022

Sergio Pereira Ruzza
CRQ: 13200008
Ceramic Technology Manager

Angela Waterkemper Vieira
P&D Coordinator