Vanguard

Suitability area product & Composition guide

| Wall | Floor | Wet areas | Pools | Materials |
|-----------|-------------------------------|-----------|-------|-----------|
| Int / Ext | Residential No ¹ | Yes | Yes | Glass |

¹ Iridis Products

Technical Characteristics

| Test UNE-EN-ISO 10545-3 | Test UNE-EN-ISO 101-92=101 | Test UNE-EN-ISO 10545-9 | Test UNE-EN-ISO 10545-12 | Test UNE-EN-ISO 10545-13:1998 Resistance to chemical attack. | | | |
|-----------------------------|----------------------------------|--|---|--|------------------------------|-----------------------------|--|
| Water Absorption. | Surface hardness. Mohs. | Resistance to thermal shocks. | Frost Resistance. | Domestic Products. | Pool water additives. | Low acid and alkalins. | High acid and alkalins. |
| None | 4 | Resistant | Resistant | GA | GA | GLA | GHA |
| Test UNE-EN-ISO 10545-14 | Test UNE-EN-ISO 10545-11=1997 | DIN 51094 | DCOF | | DIN 51130:2004 SLIP | DIN 51097 SLIP | Test UNE-ENV 12633:2003 (CTE) |
| Resistance to staining. | Cracking. | Colour Stability on exposure to light and UV rays. | Wet Dynamic Coefficient of Friction ANSI A 137.1 Standard. | | Resistance wearing shoes. | Resistance in bare feet. | Anti skid coeffi- cient, suitable for outdoor use and swimming pools. |
| Class 5 | Resistant | Resistant | | | | | |

Packing

| Sheet Hoja | 4,7 mm - 0.185" Thickness | 311x467 mm - 12.24"x18.38" | 1,3 kg - 2.86 lb | |
|-----------------------------------|---------------------------|----------------------------|------------------------|--|
| Box Caja | Box Caja 14 Sheets | | 18,7 kg - 41.22 lb | |
| Pallet Palet 60 Boxes | | 121,8 m² - 1311.04 sqft | 1131,9 kg - 2495.41 lb | |
| Euro Pallet Euro Palet 50 Boxes | | 101,5 m² - 1092.53 sqft | 957,1 kg - 2110.04 lb | |



Made in Spain

98% Recycled Glass



Ø

Green & Sustainable Products

All ONIX 98% recycled glass mosaics series are made of molten glass. Molten glass characteristics may include irregular edges and small variations in size. These characteristics are inherent to the product and to the standard production. The small size and shape variations can affect the grout joint appearance and enhance the natural aspect of these products.

