

COLOR: GREY OAK
Surface: matt surface
Material: SPC click flooring
Dimension: 1220x183x4mm
Wear layer: +1.5MM IXPE
Wear layer: 0.5mm



TEST ITEM	TEST METHOD	REQUIREMENT	TEST RESULT	VERDICT
SIZE	EN 14041:2004/AC:2006 & EN649:2011 & EN ISO 24346:2012	LENGTH: 1220 MM WIDTH:183MM	SEE RESULT	PASS
THICKNESS	EN 14041:2004/AC:2006 & EN649:2011 & EN ISO 24346:2012	NOMINAL THICKNESS:5.5MM	AVE: 5.50 MAX.: 5.54 MIN.: 5.49	PASS
THERMAL CONDUCTIVITY	EN 14041:2004/AC:2006 Clause 4.7 & EN 12667:2001	0.124 W/(m·K)	0.124 W/(m·K)	PASS
FOMMALDEHYDE	WITH REFERENCE TO EN 14041:2004/AC:2006 & EN 717-1:2004, ANALYSIS WAS PERFORMEDBY UV-VIS.	E1	0.08mg/m3	PASS
FIRE CLASSIFICATION	EN ISO 9239-1	S1	CRITICAL FLUX (kWV/m2): 10.3	PASS
			SMOKE (%xMINUTES): 114.5	PASS
DYNAMIC COEFFICIENT OF FRICTION	EN 13893:2002	THE FLOOR COVERING INTENDED TO BE USED IN DRY AND NON-CONTAMINATED CONDITIONS SHALL HAVE A DYNAMIC COEFFICIENT OF FRICTION OF ≥ 0.30 WHEN TESTED EX-FACTORY UNDER DRY CONDITIONS IN ACCORDANCE WITH EN13893 AND SHALL BE DECLARED AS TECHNICAL CLASS DS	X DIRECTION: 0.38	PASS
			Y DIRECTION: 0.39	PASS