















NAME OF SERIES OR ITEM NUMBER	KC GR302 (DT3388)
MATERIAL ( CERAMIC, PORCELAIN, DOUBLE LOADING, SOLUBLE SALT, SALT&PEPER, COLOR BODY )	PORCELAIN
BODY ( RED, WHITE , FULL BODY)	FULL BODY
VISUAL FINISH (MATT OR GLAZED, LAPATTO)(视觉上)	MATT
SURFACE FINISH (ROUGH OR POLISH) (触觉)	ROUGH
Producing Technique (ROTO COLOR, INJECT, SCREEN PRINTING )	INJECT PRINTING
LAST UPDATE	2025-3-31



TECHNICAL CHARACTERISTICS CARACTERISTICAS TECNICAS		PORCEMIKA VALUES / VALORES	NORMA ISO 13006 REQUISITOS / REQUIREMENTS PAVIMENTOS	TEST METHOD AS PER IOS NORM TEST DE ACUERDO A
	LENGTH AND WIDTH DIMENSIONES (MM)	-0.07-0.07%	±2.5%	UNI EN ISO 10545-2
	STRAIGHTNESS OF SIDE RECTITUD LATERAL (MM)	-0.06-0.08%	±0.5%	UNI EN ISO 10545-2
	RECTANGULAR SQUARENESS ORTOGONALIDAD (MM)	-0.05-0.06%	±0.6%	UNI EN ISO 10545-2
	SURFACE FLATNESS PLANARIDAD (MM)	-0.06-0.00%	±0.5%	UNI EN ISO 10545-2
	THICKNESS ESPESOR (MM)	-1.1-0.6%	±5%	UNI EN ISO 10545-2
	WATER ABSORPTION ABSORCION DE AGUA	0.08%	E ≤ 0.50 % for Porcelain 0,5% < E ≤ 3%, Gress 3% < E ≤ 6%, Semigres 6% < E ≤ 10 %, Semiporoso 10% < E ≤ 20 %,poroso (ceramic wall)	UNI EN ISO 10545-3
	BENDING RESISTANCE RESISTENCIA A LA FLEXION	40MPA	≥35Mpa for Porcelain ≥ 12 Mpa for Ceramic	UNI EN ISO 10545-4
	BREAKING STRENGTH FUERZA DE ROTURA	8321N	≥1500N for Porcelain ≥ 600 N for Ceramic	UNI EN ISO 10545-4
	CHEMICAL RESISTANCE RESISTENCIA A PRODUCTOS QUIMICOS	GA	≥ GB	UNI EN ISO 10545-14
	STAIN RESISTANCE RESISTENCIA A LA MANCHAS	5	≥ 3 CLASS	UNI EN ISO 10545-14
	DEEP ABRASION RESISTANCE (TECHNICAL PORCELAIN) RESISTENCIA A LA ABRASION PROFUNDA	/	< 175 mm² High Traffic <393 mm² Moderate Traffic <649 mm² Medium Traffic <393 mm² Light Traffic <393 mm² Very Light	UNI EN ISO 10545-6
	MOHS HARDNESS SUPERFICIAL (ESCALA MOHS)	DUREZA /	MOHS 1-10	UNI EN ISO 10545-7
	SHADE VARIATION CLASS DE TONALIDAD	VARIACION V2	V1-V4	DIN 51094

PACKING INFORMATION  
INFORMACION DE EMPAQUE

SIZE FORMATO	M2/BOX M2/CNT	PCS./BOX PZA./CAJA	BOX/PALLET CAJA/PALETA	M2/PALLET M2/PALETA	KG/BOX KG/CAJA	KG/PALLET KG/PALETA
300x300x18mm	0.72	8	72	51.84	27.4	1992.8

Se aconseja al colocar, mezclar las piezas de varias cajas. Verificar antes de colocar: tonalidad, calibre y clase. No se admiten reclamaciones referentes al material colocado.

RECOMENDACIONES

.Aconsejamos para su conservación que: una vez colocados, retiren los restos del material de colocación (cementos, etc) con una esponja y abundante agua, sin frotar sobre las piezas con ningún material abrasivo.

.En posteriores limpiezas, no utilizar nunca detergentes en polvo, soluciones ácidas o alcalinas ni estropajos abrasivos. Es suficiente una esponja, abundante agua y/o jabón líquido neutro.